

编号 : SZIN1810011995PS_CN

日期 : 2018-10-17

页码 : 1 of 5

客户名称: 中山市东升镇达美塑料粉末厂

客户地址: 中山市东升镇东成路 130路 1号

下列样品由客户提供及确认:

样品名称 : 哑光黑色纯聚酯粉末 (00B) SGS参考号 : GZIN1712051057MR_CN

产品规格 : 72CM*138CM

生产商 : 中山市东升镇达美塑料粉末厂

购买商 :

材质牌号 : 铁板

其他信息 : CPP-50231A 收样日期 : 2018-09-06

测试开始时间 : 2018-09-09 测试结束时间 : 2018-10-17

测试结果 : 请见下页

通标标准技术服务有限公司深圳分公司 检测中心 授权签名

f (86-755) 83197625 e sgs.china@sgs.com



李腊元

授权签字人



This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/en/Terms-and-Conditions.aspx and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Document.aspx. Attention is drawn to the limitation of liability indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflect the Company's findings at the time of its intervention only and within the limits of Client's interventicions, if any. The Company's sole responsibilities to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior uniten approval of the Company. Any unauthorize alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fulles extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

retained for 30 days only.

Attention: To check the authenticity of testing /inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN_Doccheck@sgs.com

SSS 8tds, No. 4, Jangton holdstid Part, No. 401, Jha Root, Bantan , Longang District, Shenzher, Crina 518129 t (86-755) 25328282 f (86-755) 83197625 www.sgsgroup.com.cn

中国·深圳·龙岗区坂田吉华路430号江灏工业园4栋SGS大楼 邮编: 518129 t (86-755) 25328282



编号 : SZIN1810011995PS_CN

日期 : 2018-10-17

页码 : 2 of 5

结果总结:


序号	测试项目	测试方法	结果		结论
			ΔE*ab	0.2	
1	光老化试验-紫外辐射	ASTM G154-12a循环	变色等级	0	
1	暴露	1 & GB/T 1766-2008	失光率	10%	/
			失光等级	1	

备注: 合格: 达到要求

不合格: 未到达要求

/: 不下判定

原样照片:







编号 : SZIN1810011995PS_CN

日期 : 2018-10-17

页码 : 3 of 5

测试项目: 光老化试验-紫外辐射暴露

样品描述: 带涂层的

测试方法: ASTM G154-12a循环 1 & GB/T 1766-2008

测试条件:

测试循环:

ASTM G154-12a循环 1

灯管类型: UVA-340

光照: 8h, (60±3)℃ BPT, 0.89W/(m² •nm)@340nm

冷凝: 4h, (50±3)℃ BPT

暴露时间: 500h

测试结果:

样品	ΔE*ab (见备注 1)	变色等级 (见备注2)	失光率	失光等级 (60°几何条件,见备注3)
1	0.2	0	10%	1





编号 : SZIN1810011995PS_CN

日期 : 2018-10-17

页码 : 4 of 5

备注:

1. ΔE*ab 用积分球分光光度计测量,使用 D65标准光源,10°观察角,结果为包含镜面反射,25mm孔 径。

2.变色等级参照 GB/T 1766-2008表 5(仪器法),如下:

等级	色差值/△E*	变色程度
0	≤1.5	无变色
1	1.6~3.0	很轻微变色
2	3.1~6.0	轻微变色
3	6.1~9.0	明显变色
4	9.1~12.0	较大变色
5	>12.0	严重变色

3.失光等级参照 GB/T 1766-2008表 4, 如下:

等级	失光程度(目测)	失光率/%
0	无失光	≤3
1	很轻微失光	4~15
2	轻微失光	16~30
3	明显失光	31~50
4	严重失光	51~80
5	完全失光	>80

4.以上测试项目是在 SGS内部实验室进行。

5.此测试报告是报告编号 SZIN1511011982PS的中文译本,中英文版本如有歧义,概以英文版为准。






编号 : SZIN1810011995PS_CN

日期 : 2018-10-17

页码 : 5 of 5

测试照片:



设备信息:

设备	型号	设备编号	校准日期	下次校准日期
荧光紫外老化机	QUV-Se	GZMR-AG-E059	2018-07-13	2019-07-12
光泽度仪	4446	GZMR-AG-E119	2018-05-29	2019-05-28
积分球光度计	Color i7	GZMR-AG-E155	2018-05-18	2019-05-17

********报告结束*******



This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/en/Terms-and-Conditions.aspx and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Document.aspx. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

**Attention: To check the authenticity of testing /inspection report & certificate, please contact us at telephone (85,755) 8307 1443.

uthenticity of testing /inspection report & certificate, please contact us at telephone: (86-755) 8307 1443,